



















Kayanol

Kayanol	%o.w.f.	色見本 Wool	溶解度 g/L Solubility	耐光 Light : JIS	洗濯 Washing : JIS (A-2 : 50°C)			ポットイング Potting:JIS (100°C×1 時間)		
					変退色	Wool	Cotton	変退色	Wool	Cotton
Yellow N5G	1.2		100 ↑	5	3-4	4-5	5	4-5	1-2	5
Yellow N3R	1.1		100 ↑	5	3-4	4	4-5	4-5	2	5
Floxine NK(N)	0.6		60	4-5	1-2	2-3	4-5	3-4	1	4-5
Blue NR	0.7		15	4	2-3	2-3	4	4	1	4-5
Blue N2G(C)	1.1		70	5	1	2-3	2-3	3	1	4-5
Cyanine Green G	1.0		70	5-6	2-3	5	5	4	2	5
Navy Blue R	0.8		100 ↑	4	3	3-4	4-5	3	3-4	4-5

Kayanol Milling

Kayanol Milling	%o.w.f.	色見本 Wool	溶解度 g/L Solubility	耐光 Light : JIS	洗濯 Washing : JIS (A-2 : 50°C)			ポットイング Potting:JIS (100°C×1 時間)		
					変退色	Wool	Cotton	変退色	Wool	Cotton
Yellow 5GW	2.4		70	6	5	4-5	5	4-5	2	4-5
Yellow O	1.6		100	5-6	4	4-5	4-5	4-5	2-3	4-5
Scarlet FGW	1.0		60	3-4	4 ^B	5	4-5	4-5	4	4-5
Red BW	0.8		100 ↑	3-4	4-5	5	5	4-5	4	4-5
Violet FBW	1.3		100	5-6	4	5	5	4-5	3	4-5
Ultra Sky SE	1.4		100 ↑	5	3	4-5	4-5	5	2	4-5
Blue BW	1.2		100	4-5	4 ^Y	5	5	4 ^Y	4	5
Blue GW	1.6		50	4-5	4 ^Y	4-5	4-5	4 ^Y	2-3	5
Green GW	1.1		25	5	4 ^Y	5	5	4-5	3-4	5
Green 5GW	1.1		80	5	4	5	5	4-5	3-4	5
Black TLB	4.0		80	5-6	4	4	1-2	4	1-2	4-5

Kayakalan

Kayakalan	%o.w.f.	色見本 Wool	溶解度 g/L Solubility	耐光 Light : JIS	洗濯 Washing : JIS (A-2 : 50°C)			ポットイング Potting:JIS (100°C×1 時間)		
					変退色	Wool	Cotton	変退色	Wool	Cotton
Yellow GL 143	1.0		50	8	4-5	4-5	5	4-5	2-3	5
Bordeaux BL	1.3		100	6-7	5	4-5	5	4-5	1-2	4-5
Grey BL 167	1.2		100	6	3-4	4-5	5	4	2	4-5
Black 2RL	3.2		50	7	4-5	4-5	5	4-5	3	4-5
Black BGL	4.0		100	7	4-5	4-5	4-5	4-5	3	4-5

Kayalax

Kayalax	%o.w.f.	色見本 Wool	溶解度 g/L Solubility	耐光 Light : JIS	洗濯 Washing : JIS (A-2 : 50°C)			ポットイング Potting:JIS (100°C×1 時間)		
					変退色	Wool	Cotton	変退色	Wool	Cotton
Navy BW	1.6		50	5-6	4-5	4-5	5	4-5	3	5

染色条件 Dyeing condition
 染色法 Dyeing Method : 浸染 Exhaustion-Dyeing
 被染物 Material : 羊毛 トロピカル Scoured and unbleached wool
 浴比 Liquor ratio : 1:20 (20:1)
 温度/時間 Temperature/Time : 100°C×30min. → 水洗 Water rinsing
 染色 pH Dyeing pH :

	Kayanol	Kayanol Milling	Kayakalan, Kayalax
酢酸 Acetic acid	5%o.w.f.	2%o.w.f.	1%o.w.f.
酢安 Ammonium acetate	1%o.w.f.	3%o.w.f.	5%o.w.f.