

Kayarus

Kayarus	%o.w.f.	色見本 Rayon	溶解度 g/L Solubility	Fix 処理変色 Change in shade by fixing treatment	耐光 Light :JIS	洗濯 Washing : JIS (A-2 : 50°C) Fixing treatment		
						変退色	Rayon	Cotton
Light Yellow F8G	2.0		80	4-5	4	4 ^G	4-5	5
Yellow PG	2.0		50	4-5	5	4	4	5
Supra Yellow GLS	2.0		30	4 ^R	6	4-5 ^G	5	5
Supra Yellow RL	2.0		80	4	6-7	4-5	5	5
Supra Orange 2GL 125	2.0		100	4 RD	5	5	5	5
Supra Brown GTL	2.0		70	4 ^Y	4-5	5	5	5
Supra Brown B2R	2.0		45	4 ^R	3-4	5	5	5
Light Scarlet F2G	2.0		20	3 ^Y	4	5	4-5	5
Light Red F5G	2.0		100	4	3-4	5	5	5
Supra Red BWS	2.0		100	4-5	4	4-5	4	5
Light Rose FR	2.0		100	3-4 ^B	2	5	5	5
Supra Rubine BL	2.0		60	2-3 ^B	6	5	5	5
Supra Violet 5BL conc	2.0		4	2-3 ^B	5-6	4-5 ^R	5	4-5
Supra Blue MRG	2.0		40	3 ^G	4	4-5	4-5	4-5
Supra Blue CRL	2.0		40	3	4	4-5	4-5	4-5
Supra Blue BGL New	2.0		30	4	4	4-5	4-5	4-5
Supra Blue 4BL New	2.0		40	4	4	4-5	4-5	4-5
Supra Green F4G	2.0		50	3-4 ^B	5	4-5 ^Y	5	5
Cupro Green G※	2.0		20	2 ^B	5-6	4-5 ^{VS}	5	5
Supra Grey CGL	2.0		70	4 ^R	7	5	5	5
Black AR-503	8.0		40	4	6	4-5	5	4-5
Black B 160※	4.0		20	3-4 ^R	7	4-5 ^R	5	5
Black B 300※	2.0		20	3-4 ^R	7	4-5 ^R	5	5
Black B 400※	1.6		20	3-4 ^R	7	4-5 ^R	5	5

フィックス処理 Fixing : ポリアミン系フィックス剤 Polyamine fixing
 含銅ポリアミン系フィックス剤 Copper-containing polyamine
 (※) Kayarus Cupro Green G, Kayarus Black B series

染色条件 Dyeing condition

染色法 Dyeing Method : 浸染 Exhaustion-Dyeing
 被染物 Material : ビスコースレーヨン Viscose rayon
 浴比 Liquor ratio : 1:20 (20:1)
 芒硝 Glauber's Salt : 10g/L (15g/L for Black)
 ソーダ灰 Soda ash : 1.0%o.w.f. for Black B series only
 温度/時間 Temperature/Time : 90°C×45min. → 水洗 Water rinsing

Kayacelon C

Kayacelon	%o.w.f.	色見本 Cotton	溶解度 g/L Solubility	Fix 処理変色 Change in shade by fixing treatment	耐光 Light : JIS	洗濯 Washing : JIS (A-2 : 50°C) Fixing treatment		
						変退色	Cotton	Rayon
Yellow C-2RL	2.0		25	4	5	4	3	5
Rubine C-BL	2.0		50	3	5	4-5	3-4	5
Blue C-2R	2.0		40	2-3 ^{GC}	4	4-5	4-5	5
Blue C-3GL	2.0		40	4	5	4-5	4	5

フィックス処理 Fixing : ポリアミン系フィックス剤 Polyamine fixing

染色条件 Dyeing condition

染色法 Dyeing Method : 浸染 Exhaustion-Dyeing
 被染物 Material : 無シル綿 Non-mercerized cotton
 浴比 Liquor ratio : 1:20 (20:1)
 芒硝 Glauber's Salt : 10g/L
 染色 pH Dyeing pH : 5.5
 温度/時間 Temperature/Time : 130°C×45min. → 水洗 Water rinsing